

L/AS NBR

ANTIGASOLINA RESPETUOSA CON EL MEDIO AMBIENTE

NBR FOR UNLEADED FUEL



- Apto para gasolina verde sin plomo gasolina súper.

It is suitable for contact with unleaded petrol.











USO APPLICATIONS






Alto contenido en NBR y ACN. Apto para el contacto con gasolina verde sin plomo, gasolina súper, gasóleo y aceites en general. Excelente resistencia al envejecimiento y resistencia moderada a las fluctuaciones de temperatura. Buena permeabilidad a los gases.





Superficie: Lisa/Lisa o, a petición, I.T./I.T.

High NBR and acn content. It is suitable for contact with unleaded petrol, super unleaded petrol, diesel and oil in general. It offers excellent resistance against ageing and fair resistance against temperature ranges. Good permeability to gas.

 mm	STOCK	 m	 m
1	✓	1,4	20
1,5	✓	1,4	15
2	--	1,4	15
2,5	✓	1,4	10
3 ÷ 10	--	1,4	10
12 ÷ 20	--	1,4	5
25 ÷ 50	--	1	1

 DUREZA HARDNESS	 CARGA DE ROTURA TENSILE STRENGTH	 ELONGACIÓN ELONGATION	 LACERACIÓN TEAR	 COMPRESSION 24h - 70°C
Norme / Norms: ASTM D2240	Norme / Norms: ASTM D412	Norme / Norms: ASTM D412	Norme / Norms: ASTM D624	Norme / Norms: ASTM D395-B
65 Shore A ± 5	100 kg/cm ²	350%	55 kg/cm	35%

ENVEJECIMIENTO TÉRMICO THERMAL AGING			ENVEJECIMIENTO EN ACEITE	
 DUREZA HARDNESS	 CARGA DE ROTURA TENSILE STRENGTH	 ELONGACIÓN ELONGATION	 CAMBIO DE VOLUMEN VOLUME CHANGE	 CAMBIO DE VOLUMEN VOLUME CHANGE
Norme / Norms: ASTM D573	Norme / Norms: ASTM D573	Norme / Norms: ASTM D573	Norme / Norms: ASTM D471	Norme / Norms: ASTM D471
≤ +5 Shore A	≤ - 20%	≤ - 20%	≤ -10%	≤ +10%

		
	1,25 gr/cm ³	-30°C / +110°C -22°F / +230°F