

L/BA SBR (D.M. 174)

BLANCA

FDA



- **Cumple los Decretos Ministeriales 174 de 6/4/2004 y 21/3/1973 y la Lista 177.2600 de la FDA.**
It complies with the ministerial decess 174 dated 6/4/2004 and FDA dated 21/3/1973.



USO APPLICATIONS

Adecuado para el contacto en instalaciones fijas de captación, tratamiento, suministro y distribución de agua destinada al consumo humano. Cumple el Decreto Ministerial 174 de 6/4/2004 y 21/3/1973 y la Lista FDA 177.2600. No es adecuado en contacto con sustancias aceitosas o grasas. Especialmente recomendado cuando se necesita limpieza y estética, de hecho, este caucho no mancha. Disponible el certificado de aptitud para el uso con producto alimenticio.

Superficie: Lisa/Lisa o, a petición, I.T./I.T.

Can be used in contact with stationary captation systems, treatment, carrying and distribution of water intended for human consumption. It complies with the ministerial decree 174 dated 6/4/2004 and 21/3/1973 and the FDA-list 177.2600. It is not suitable for contact with oily or greasy substances. In particular, it is recommended for strict hygiene and aesthetic equirements.

In fact, this rubber is stain-proof. Food safety certificate available.

Surface: Smooth/Smooth or on request I.T./I.T.



STOCK



mm

m

m

1 / 1,5 / 2	✓	1,4	10
2,5	--	1,4	10
3 ÷ 8	✓	1,4	10
10	✓	1,4	5
12 / 15	--	1,4	5
20	✓	1,4	5
25 ÷ 50	--	1	1



DUREZA HARDNESS

Norme / Norms:
ASTM D2240

60 Shore A ± 5



CARGA DE ROTURA TENSILE STRENGHT

Norme / Norms:
ASTM D412

80 kg/cm²



ELONGACIÓN ELONGATION

Norme / Norms:
ASTM D412

250%

Declaración de conformidad disponible.
Declaration of compliance is available.



1,5 gr/cm³



-25°C / +80°C
-13°F / +176°F