



# L/TH SBR

TODO CAUCHO PREMIUM  
PREMIUM






- **Adecuado para el uso actual.**  
Suitable for current applications.



**USO  
APPLICATIONS**

Adecuado para un uso cotidiano en el que no se requiere una resistencia especial para agentes atmosféricos, aceites y calor.  
**Superficie:** Lisa/Lisa.

Suitable for current applications without particular resistance requirements against atmospheric agents, oil and heat.  
**Surface:** Smooth/Smooth

 mm	STOCK	 m	 m
1	✓	1,2	10
1,5	✓	1,2	10
2	✓	1,2	10
2,5	--	1,2	10
3 ÷ 10	✓	1,2	10
12 / 15 / 20	--	1,2	10



**DUREZA  
HARDNESS**

Norme / Norms:  
ASTM D2240

70 Shore A ± 5



**CARGA DE ROTURA  
TENSILE STRENGTH**

Norme / Norms:  
ASTM D412

40 kg/cm<sup>2</sup>



**ELONGACIÓN  
ELONGATION**

Norme / Norms:  
ASTM D412

250%



1,5 gr/cm<sup>3</sup>



-25°C / +70°C  
-13°F / +158°F