



L/CS NBR

ANTIOLIO SPECIAL

FOR HIGH TEMPERATURE



- **Eccezionale resistenza agli oli.**
Exceptional resistance against oil.






IMPIEGO APPLICATIONS

Elevatissimo contenuto di NBR e ACN. Studiata appositamente per pressatura di pelli in genere. Infatti è una gomma con eccezionale resistenza agli oli in presenza di temperatura con punte massime di 140/150°C.






Superficie: Liscia/Liscia o a richiesta I.T./I.T.






Very high NBR and ACN content. It was specifically designed for hide pressing in general. In fact, this rubber offers exceptional resistance against oil in the presence of high temperatures with maximum peaks of 140/150°C.





Surface: Smooth/Smooth or on request I.T./I.T

 mm	STOCK	 m	 m
1 / 1,5 / 2 / 2,5	--	1,2	10
3 ÷ 10	--	1,2	10
12 ÷ 20	--	1,2	5
25 ÷ 50	--	1	1

SPECIFICHE TECNICHE TECHNICAL SPECIFICATIONS

 DUREZZA HARDNESS	 CARICO ROTTURA TENSILE STRENGTH	 ALLUNGAMENTO ELONGATION	 LACERAZIONE TEAR	 COMPRESIONE COMPRESSION 24 h - 70°C
Norme / Norms: ASTM D2240	Norme / Norms: ASTM D412	Norme / Norms: ASTM D412	Norme / Norms: ASTM D624	Norme / Norms: ASTM D395-B
60 Shore A ± 5	100kg/cm ²	250%	35 kg/cm	30%

INVECCHIAMENTO TERMICO THERMAL AGING			INVECCHIAMENTO IN ACQUA AGING IN WATER	INVECCHIAMENTO IN OLIO AGING OF OIL
 DUREZZA HARDNESS	 CARICO ROTTURA TENSILE STRENGTH	 ALLUNGAMENTO ELONGATION	 VARIAZIONE VOLUME VOLUME CHANGE	 VARIAZIONE VOLUME VOLUME CHANGE
Norme / Norms: ASTM D573	Norme / Norms: ASTM D573	Norme / Norms: ASTM D573	Norme / Norms: ASTM D471	Norme / Norms: ASTM D471
≤ +5 Shore A	≤ - 10%	≤ - 10%	± 2%	≤ +25%

		
	1,20 gr/cm ³	-30°C / +120°C 140°C -22°F / +248°F 284°F